

Contract No.:

Sieve

Sizes (mm)

150.0

106.0

75.0

53.0

37.5

26.5

22.4

19.0

16.0

13.2

9.5

6.7 4.75

2.36

1.18

0.600

0.300

0.150

0.075

Grain Size Analysis

Sample

100

100

100

100

100

100

100

100

100

100

100

100

100

96.7

74.8

46.5

18.1

3.5

1

Percent Passing

Specification

100 - 100

95 - 100

80 - 100

50 - 85

25 - 60

10 - 30

0 - 10

0-3

SNC · LAVALIN

Grain Size Analysis Test Report

Strada Harbour Aggregates 2017 - Laborat Date: 17-1235-01 **Project Description:**

May 01, 2017

Project Location:

SAMPLE DATA

Material:

Project No.:

Concrete sand

Date Sampled:

Apr 27, 2017

Time Sampled:

Sample Type:

Shovel

Sample Location:

Strada # 2852

Lot:

Sublot:

Source:

Strada Aggregates-Hillsburgh Pit

Sampled By:

Client

LAB DATA

Lab No.:

2092

Date Tested:

Apr 28, 2017

Specification:

OPSS 1002, Concrete sand (Pit)

PARTIC	IF	ANAI	VCIC
FARIIG	ᆫ	WINW	- 1010


TEST	Sample	Specification
Percent Crushed:		
% Asphalt Coated:		
% Flat and Elongated		


		_		
WA	SH	PAS!	3 0	075mm

TEST	Sample	Specs
Wash Pass 0.075 mm:		
FINENESS MODULUS	2.60	

Comments:

Sample: Specs:





Data presented hereon is for the sole use of the stipulated client. SNCL is not responsible, nor can be held liable, for use made of this report by any other party, with or without the Innowledge of SNCL. The testing services reported herein have been performed by a SNCL technician to recognized industry standards, unless otherwise noted. No other warranty is made. This data does not include or represent any interpretation or opinion of specification compliance or material suitability. Should engineering interpretation be required, SNCL will provide it upon written request.

Project Manager: Nick Sibilia